



Typical Properties Sheet

2/2/2015

Product: **N4194**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft3)	5	ASTM D-1056
Compressive Resistance – @25%	2 - 5 psi	ASTM D-1056
Compression Set (%) 50%	50	ASTM D-1056
Tensile Strength (psi)	90 min	ASTM D-412
Water Absorption (lbs / ft2)	5% max	ASTM D-1667
Elongation (%)	150 min	ASTM D-412
Classification	2C1	ASTM D-1056-91
Type/Grade	SCE 41	ASTM-D-1056-67-68
Flammability	pass pass (1/16" min)	FMVSS302 UL94 HF-1
Polymer Blend	Neoprene/ EPDM	
Temperature Resist.	-40 to 250	

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com