



Typical Properties Sheet

2/2/2015

Product: **I-Cell**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Natural	
Density (lbs / ft3)	2.0	ASTM D 3575
Compressive Strength – @25%	5	ASTM D 3575
Compression Set (%)	<30	ASTM D 3575
Tensile Strength (psi)	43	ASTM D 3575
Tear Resistance (lbs/inch)	12	ASTM D 3575
Water Absorption (lbs / ft2)	<0.1	ASTM D 3575
Working Temperature Range	-70 to 175deg F	
Elongation (% to break lengthwise)	210	ASTM D 3575-93

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com