



# Typical Properties Sheet

11/8/2018

Product: **60PPI**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Charcoal Grey	
Density (lbs / ft <sup>3</sup> )	1.30 - 1.60	ASTM D-3574-01
Compression Deflection @ 25% (psi)	0.4	ASTM D-3574-01
Tensile Strength (psi)	13	ASTM D-3574-01
Elongation (%)	120	ASTM D-3574-01
Tear Strength (lbs / lin inch)	2.0	ASTM D-3574-01
Flame Resistance	N/A	
Pore Size (ppi)	55 - 65	Visual Call

This foam is an ether

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

**WARNING: URETHANE FOAM IS FLAMMABLE!**

**Urethane Foam should not be exposed to open flame or other ignition sources.  
Urethanes burn rapidly with great heat and release gases which are extremely hazardous.**

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

**[www.amconfoam.com](http://www.amconfoam.com)**