



Typical Properties Sheet

6/21/2018

Product: **EV45-CN**

<u>Physical Property</u>	<u>Value</u>	<u>Test Method</u>
Color	Black	
Density (lbs / ft ³)	2.8 (50 kg/m ³)	ASTM D3575-91
Compression Stress-Strain – @25% (psi) @50%	10 (61 kPa) 13 (128 kPa)	ASTM D3575-91
Comp Set (%) 50% comp 24hr	14.5	ASTM D3575-91
Tensile Strength (psi)	80 (575 kPa)	ASTM D3575-91
Tear Resistance (lbs/in.)	17 (1240 N/m)	ASTM D3575-91
Recommended operating temperature range	-95 to 150 deg F (-70min, 65.5max cel)	Internal
Thermal Conductivity (W /m.K)	0.038	ISO 8302 1991
Surface Resistivity (ohms/sq.)	5 x 10 ³	ASTM D991-89

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, Amcon does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

5360 Main St. NE Minneapolis, MN 55421

Ph. 888-360-8050

www.amconfoam.com